



TECHNICAL DATA SHEET

Product	OMNI POLYMERS MDPE PRO1100T20
Product no.	1100RM01AS1320
Base Polymer	Medium Density Polyethylene
Special Features	100% post-consumer recycled material
Filtration screen	230-260 µm
Forms	Granulate
Appearance	Grey
Processing method	Injection moulding
Application Area	Injection moulded parts, various

TYPICAL PROPERTIES AND CHARACTERISTICS

Physical Properties	Method	Unit	Value
MFI 190°C/5kg	ISO 1133	g/10 min	4.7
MFI 230°C/2,16kg	ISO 1133	g/10 min	2.7
Density	ISO 1183	g/cm ³	1.09
Impact Properties			
Impact test Izod (notched) +23°C	ISO 180/A	kJ/m ²	10.1
Impact test Charpy (notched) +23°C	ISO 179-1/1eA	kJ/m ²	10.1
Tensile Properties			
Tensile strength modulus	ISO 527-2/1A/1	MPa	362
Tensile strength	ISO 527-2/1A/50	MPa	3.86
Tensile elongation at break	ISO 527-2/1A/50	%	354

Disclaimer: the values indicated on this technical data sheet are to be used as guides and not specifications. They are representative values only and not binding minimum or maximum figures. These test values have been determined on standardised test specimens and can be affected by pigmentation, mould design and processing conditions. Any information given on the chemical and physical characteristics of our products, including, without limitation, technical advice on applications, whether verbally, in writing or by testing the product, is given to the best of our knowledge and in good faith and does not exempt the buyer from carrying out their own investigations and tests in order to ascertain the product's specific suitability for the purpose intended. The buyer is solely responsible for confirming the suitability of the product for a particular application, its utilisation and processing, and must observe any applicable laws and government regulations. At all times, our standard terms and conditions of sale apply.